



# CUTBACKS

## PROPRIETARY BRANDED CUTBACK ASPHALTS SPECIFICATION TABLE

PROPERTIES	BLACKMAC	B-PAINT	MACSEAL WP	MACSEAL FC	MACPATCH	MACPATCH HC
Tests on Liquid Asphalt	min-max	min-max	min-max	min-max	min-max	min-max
Flash Point, °C		27 min	27 min			
Kinematic Viscosity, 60°C, mm <sup>2</sup> /s		100 – 200			100 – 200	500 – 650
Saybolt Furol Viscosity, 25°C, SFs	20 - 60		5 – 40	25 – 65		
Distillation Test, % of total distillate to 360°C						
to 190°C	15 min					
to 225°C	55 min					
to 260°C	75 min					
to 316°C	90 min					
Residue from Distillation, 360°C, %	45 min	50 – 75	30 min	50 – 75	67 min	67 min
Tests on Residue						
Penetration, 25°C, dmm	5 – 25	25 – 85	25 – 85			
Softening Point, R&B, °C	60 min	49 – 80	49 – 80			
Solubility in TCE, %	97.5 min	98 min	98 min			



### McASPHALT INDUSTRIES LIMITED

8800 Sheppard Avenue East T 416.281.8181 TF 1.800.268.4238  
 Toronto, ON M1B 5R4 F 416.281.8842 E info@mcasphalt.com

mcasphalt.com  
 ISO 9001/14001