

EMULSIONS

CRS-2

Product Data Sheet Typical Analysis and Specifications



Pavement
Maintenance

Last Revised: January 2016

Supply Point: Acheson

Test	Units	ASTM	Specification*		Typical Analyses
			Min.	Max.	
Density		D6937	--	--	1.010
Viscosity at 50°C (SF)	s	D7496	100	400	120.0
Residue by distillation	% by mass	D6997	65	--	68.0
Demulsibility 35 ml of 0.5% solution of dioctyl sulphosuccinate	% by mass	D6935	60	--	85.5
Sieve test	% by mass	D6933	--	0.10	0.01
24 hr. Storage Stability test	% by mass	D6930	--	1.0	0.40
Particle charge test		D7402			Positive
Tests on Residue					
Penetration at 25°C ,100g	mm/10	D5	100	250	170
Ductility at 25°C	cm	D113	60	--	60+
Solubility in TCE	%	D2042	97.50	--	99.99

* Local specifications may vary

For assistance and general inquires please contact our help line at 1-855-777-1550 or info@colasphalt.ca
Visit us at www.colasphalt.ca



Anti-Stripping
Agents



Base
Preparation



Cold Mix
Asphalt



Dust
Control



Liquid
Asphalts



Pavement
Bonding



Pavement
Maintenance



Warm Mix
Asphalt