

EMULSIONS

Product Data Sheet Typical Analysis and Specifications

Colasphalt
HFHR



Pavement
Maintenance

Last Revised: January 2016

Supply Point: Acheson

Test	Units	ASTM	Specification*		Typical Analyses
			Min.	Max.	
Density at 25°C	Kg/L	D6937	--	--	0.975
Residue by distillation	% by mass	D6997	85	--	86.0
Oil portion of distillate	% by vol.	D6997	--	2	0.50
Kinematic Viscosity at 60°C	mm ² /s	--	--	--	1500
Tests on Residue					
Penetration at 25°C ,100g	mm/10	D5	500	--	500+
Apparent Viscosity at 60°C	Pa-s	D113	8	30	20
Float Test at 60°C	Seconds	D139	1200	--	1200+
Solubility in TCE	%	D2042	97.50	--	99.99

* Local specifications may vary

For assistance and general inquires please contact our help line at 1-855-777-1550 or info@colasphalt.ca
Visit us at www.colasphalt.ca



Anti-Stripping
Agents



Base
Preparation



Cold Mix
Asphalt



Dust
Control



Liquid
Asphalts



Pavement
Bonding



Pavement
Maintenance



Warm Mix
Asphalt