

LIQUID ASPHALTS

PG 64-34P

Product Data Sheet

Typical Analysis and Specifications



Liquid
Asphalts

Last Revised: January 2016

Supply Point: Acheson

	Test	Method	Specification	Test Temperature	Typical Result	Units
Original	Flash Point	T 48	min 230°C		280	°C
	Rotational Viscosity	T 316	max 3000cP	135°C	447.5	cP
	Dynamic Shear	T 315	min 1.00 kPa	64°C	1.163	kPa
	Predicted Failure				66.46	°C
	Specific Gravity	T 228		15°C	1.038	
RTFO	Mass Change	T 240	max 1.00%	135°C	-0.602	%
	Dynamic Shear	T 315	min 2.20 kPa	64°C	2.887	kPa
	Predicted Failure				66.74	°C
PAV	<i>PAV aging conducted at 100°C as per AASHTO R 28</i>					
	Dynamic Shear	T 315	max 5000 kPa	16°C	2250	kPa
	Predicted Failure				12.87	°C
	Creep Stiffness	T 313	max 300 MPa	-24°C	251	MPa
	m-value	T 313	min 0.300	-24°C	0.321	
	Predicted Failure				-35.47	°C
	Direct Tension Testing					
	Failure Strain	T314	min 1.00%	-24°C	2.14	%
	Failure Stress	T314		-24°C	3.24	MPa
	Critical Cracking				-36.0	°C

Laboratory Recommended Ranges	Low	High
Mixing Temperature Range, Degrees C	155	161
Compaction Temperature Range, Degrees C	144	149

Also Available



Warm Mix
Asphalt



Anti-Stripping
Agents

For assistance and general inquires please contact our help line at 1-855-777-1550 or info@colasphalt.ca

Visit us at www.colasphalt.ca



Anti-Stripping
Agents



Base
Preparation



Cold Mix
Asphalt



Dust
Control



Liquid
Asphalts



Pavement
Bonding



Pavement
Maintenance



Warm Mix
Asphalt