

# LIQUID ASPHALTS

# PG 76-28P

## Product Data Sheet

## Typical Analysis and Specifications



Liquid  
Asphalts

Last Revised: January 2016

Supply Point: Acheson

	Test	Method	Specification	Test Temperature	Typical Result	Units
<b>Original</b>	Flash Point	T 48	min 230°C		282	°C
	Rotational Viscosity	T 316	max 3000cP	135°C	1995	cP
	Dynamic Shear	T 315	min 1.00 kPa	76°C	1.181	kPa
	Predicted Failure				77.77	°C
	Specific Gravity	T 228		15°C	1.040	
<b>RTFO</b>	Mass Change	T 240	max 1.00%	135°C	-0.620	%
	Dynamic Shear	T 315	min 2.20 kPa	76°C	3.494	kPa
	Predicted Failure				81.66	°C
<b>PAV</b>	<i>PAV aging conducted at 100°C as per AASHTO R 28</i>					
	Dynamic Shear	T 315	max 5000 kPa	28°C	974	kPa
	Predicted Failure				14.44	°C
	Creep Stiffness	T 313	max 300 MPa	-18°C	201	MPa
	m-value	T 313	min 0.300	-18°C	0.355	
	Predicted Failure				-33.07	°C
	<b>Direct Tension Testing</b>					
	Failure Strain	T314	min 1.00%	-18°C	1.24	%
	Failure Stress	T314		-18°C	2.44	MPa
	Critical Cracking				-32.5	°C

Laboratory Recommended Ranges	Low	High
Mixing Temperature Range, Degrees C	176	183
Compaction Temperature Range, Degrees C	164	168

Also Available



Warm Mix  
Asphalt



Anti-Stripping  
Agents

For assistance and general inquires please contact our help line at 1-855-777-1550 or [info@colasphalt.ca](mailto:info@colasphalt.ca)

Visit us at [www.colasphalt.ca](http://www.colasphalt.ca)



Anti-Stripping  
Agents



Base  
Preparation



Cold Mix  
Asphalt



Dust  
Control



Liquid  
Asphalts



Pavement  
Bonding



Pavement  
Maintenance



Warm Mix  
Asphalt